

# FINISHING FACTS

## COMPARISON OF HOLIDAY'S MASTER FINISH TO OTHER CATALYZED LACQUER AND LACQUER FINISHES

Conducted by an independent testing lab. All tests are 24 hour exposures to panels without covers, except for KCMA Detergent and Water Solution, which was left for 24 hours under a watch glass.

Substance	Holiday's Master Finish	Catalyzed Lacquer	Lacquer
Merthiolate	5	1	1
Fingernail Polish	5	1	1
Joy Liquid	5	5	5
Liquid Shoe Polish	5	5	1
Acetone	4	3	1
Naptha	5	5	5
Vinegar ♦	5	5	5
Rubbing Alcohol	5	1	4
Ammonia	5	5	5
Coffee ♦	5	5	5
Ink	4	3	1
Iodine	5	1	2
Mustard ♦	5	4	5
Water	5	5	5
Lemon Juice ♦	5	5	5
Orange Juice ♦	5	5	5
Grape Juice ♦	5	5	5
Tomato Catsup ♦	5	5	5
Olive Oil ♦	5	5	5
100 Proof Alcohol ♦	5	5	5
KCMA Detergent and Water Solution	5	4	5
Cold Check	passed 25 cycles	passed 25 cycles	failed

### Ratings:

5 . . . . No Effect, Excellent  
 4 . . . . Slight Effect, Very Good, Acceptable  
 3 . . . . Some Effect, Good, Not Acceptable  
 2 . . . . Strong Effect, Fair, Not Acceptable  
 1 . . . . Poor, Fail

### Notes:

Dry Film Thickness: 3.0 – 3.5 mils  
 ♦ Denotes KCMA Test

## FOIL / HPL / BANDING / PAINT CROSS REFERENCE

Foil Color	HPL	PVC Banding	Paint
Textured White	Pionite SW811	Standard White	NC32
Satin White	WA 1573-60	CP 1460-TL	NC32
Antique White Textured	WA 1572-60	CP 1578-TL	Antique White
Antique White Satin	Formica 932-58	CP 1452-TL	Antique White
Designer Almond (textured)	WA D30-60	CP 2514-TL	N/A
High Gloss White	WA 1573-1	CP 1474-TG	N/A
Cherry Pear	Pionite WX031-N	CP 5214-TL	N/A
N/A	WA D30-60	CP 2574-TL	Bone *
N/A	WA D354-60	CP 1474-TL	Winter
N/A	Pionite SW811	CP 1401-TL	Ivory
Sakura Cherry	WA 7921-38	E 7265	N/A
Sienna Wild Apple	WA 7054-60	WT 3921	N/A

### Note:

\* HPL, banding, and paint may not be an exact match. It is the dealer's responsibility to verify match. Sample available upon request.